

## Resinates

### RL IR MR 7711-L 7% H



### Iridium Resinate Solution

#### Description

RL IR MR 7711-L 7% H is a liquid precious metal solution and it contains iridium in form of dissolved organo-metallic compound.

#### Key Benefits

- Suitable to use as additive for thick film and organo-metallic pastes
- Free of lead, cadmium and nickel
- Free of phthalate
- REACH <sup>1</sup> and RoHS <sup>2</sup> compliant

#### Processing

1. When stored in a refrigerator allow product to come to room temperature prior to opening, to avoid condensation.
2. The solution is miscible with halogenated hydrocarbons, some higher alcohols (e.g. Terpineol), esters and ketones (e.g. Cyclohexanone). Not miscible with aliphatic and aromatic hydrocarbons, lower alcohols, esters and ketones.

#### Typical Properties (Solution)

Form:	Dark brown liquid
Viscosity:	100 - 500 mPas (20 °C, D = 50 sec <sup>-1</sup> )
Chem. Characterization:	Iridium sulforesinate in a mixture of organic solvents
Iridium Content <sup>3</sup> :	7.0 ± 0.3 %
Calcinated Residue:	8.2 ± 0.4 % IrO <sub>2</sub> (theoretical value)
Coverage:	Not applicable
Shelf Life:	12 months from date of shipment with correct storage (in a dry, cool (5 – 25 °C) and dark place with container tightly shut)

#### Thinner

Toluene  
Cyclohexanone

## Resinates

RL IR MR 7711-L 7% H



### Iridium Resinate Solution

- 1 REACH compliant according to the latest \*\* Annex XIV to Regulation (EC) of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments: the material does not contain any substance listed in Annex XIV.
- 2 RoHS compliant according to the latest \*\* Directives (European Union) of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions related to Pb)
- 3 Inductively coupled plasma optical emission spectrometry (ICP-OES), also referred to as Inductively coupled plasma atomic emission spectroscopy (ICP-AES), is an analytical technique used for the detection of trace metals.

\*\* See the data sheet issue date (DD/MM/YY) as reference of validity of latest edition which is available on request.

---

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Heraeus Tokmak A.S.  
Kemalpaşa O.S.B. Mah. 37. Sok. No:6  
35170 Ulucak Kemalpaşa  
İzmir TURKEY  
Tel. +90 232 8772 410  
[www.heraeustokmak.com](http://www.heraeustokmak.com)